

Radiant Rollout™ Mat with Wirsbo hePEX™ Tubing

Submittal information
Revision H: Sept. 19, 2018

Project information

Job name:	
Location:	Part no. ordered:
Engineer:	Date submitted:
Contractor:	Submitted by:
Manufacturer's representative:	Approved by:

Technical data

Materials:	Crosslinked polyethylene (PEX-a) Engel method UDELE® polysulfone (PSU) 20% glass-reinforced for ProPEX® engineered polymer (EP) fittings ¹ Acetal polymer for support strip bracing; Nylon zip ties; Brass Schrader® valve
Standard grade hydrostatic ratings (PPI):	200°F at 80 psi (93°C at 5.51 bar) 180°F at 100 psi (82°C at 6.89 bar) 73.4°F at 160 psi (23°C at 11.03 bar)
Linear expansion rate:	1.1"/10°F per 100' (27.94mm/5.56°C per 30.48m)



Product information and application use

The Radiant Rollout™ Mat features ½" or ¾" Wirsbo hePEX™ tubing that has an oxygen-diffusion barrier that meets German DIN 4726/9. The mat can include a ¾" reverse-return header with ¾" ProPEX EP fittings that is pressurized to 20 psi to ensure system integrity. The mat can also be designed without a reverse-return header. In this instance, it is not pressurized and can connect to a wall manifold such as the TruFLOW™ Classic Manifold.

✓ Description	Part number	Loops	Roll height	Roll length	Support strip bracing	Roll width	Roll weight
½" Wirsbo hePEX Radiant Rollout Mat (6" o.c.), 5 loop	M2306060000	5	2' to 4'	40' to 150'	5' wide; place every 7' length; pre-drilled anchor points; acetal polymer	5'	27.20 to 91.46 lbs.
½" Wirsbo hePEX Radiant Rollout Mat (9" o.c.), 3 loop	M2309054000	3	2' to 4'	40' to 150'	5' wide; place every 7' length; pre-drilled anchor points; acetal polymer	4.5'	18.21 to 59.17 lbs.
½" Wirsbo hePEX Radiant Rollout Mat (12" o.c.), 3 loop	M2312072000	3	2' to 4'	40' to 150'	5' wide; place every 7' length; pre-drilled anchor points; acetal polymer	6'	18.51 to 59.47 lbs.
¾" Wirsbo hePEX Radiant Rollout Mat (6" o.c.), 5 loop	M2406060000	5	2' to 4'	40' to 225'	5' wide; place every 7' length; pre-drilled anchor points; acetal polymer	5'	36.52 to 187.48 lbs.
¾" Wirsbo hePEX Radiant Rollout Mat (9" o.c.), 3 loop	M2409054000	3	2' to 4'	40' to 225'	5' wide; place every 7' length; pre-drilled anchor points; acetal polymer	4.5'	23.81 to 118.54 lbs.
¾" Wirsbo hePEX Radiant Rollout Mat (12" o.c.), 3 loop	M2412072000	3	2' to 4'	40' to 225'	5' wide; place every 7' length; pre-drilled anchor points; acetal polymer	6'	24.11 to 118.84 lbs.

Installation

At the jobsite, roll out the mat and, depending on your header/manifold selection, connect to a supply-and-return line using the attached header (optional) or connect each loop to a wall manifold (optional). Contact your local Uponor representative for more information.

Listings²

cNSFus-rfh; cNSFus-pw; cQAlus; UL; CSA; PPI TR-4; ICC-ES; IAPMO; CCMC

Codes

ICC; IPC; IMC; IRC; UPC; UMC; NSPC; HUD; UFGS; NPC of Canada; NBC of Canada

Standards

ANSI/NSF 14; ANSI/NSF 61; ASTM F876; ASTM F877; ASTM F1960; ASTM F2023; ASTM E84; CAN/ULC S102.2; ASTM E119/UL 263; CAN/ULC S101; ASTM E814/ULC S115; CSA B137.5; CSA B214; DIN 4726/9

Related applications

Radiant heating and cooling systems
Snow and ice melting systems
Permafrost protection systems
Turf conditioning systems

Contact information

Uponor Inc.
5925 148th Street West
Apple Valley, MN 55124 USA
Phone: 800.321.4739
Fax: 952.891.2008
uponorpro.com

Uponor Ltd.
6510 Kennedy Road
Mississauga, ON L5T 2X4 CANADA
Phone: 888.994.7726
Fax: 800.638.9517
uponorpro.com

¹ProPEX® is a registered trademark of Uponor Inc. ProPEX™ is a trademark of Uponor Ltd.

²Visit listing agency's website for complete information.